

TECHNICAL DATA SHEET

CODE: 01-12032019

NAME: 01-12032019 - HYDROINT FONDO A SPRUZZO

GROUP: WATER-BASED SINGLE-COMPONENT CLEAR PRIMER

CHARACTERISTICS

Fondo monocomponente trasparente all'acqua, per applicazioni a spruzzo, su legno o materiali legnosi caratterizzato da una ottima copertura, ottimo carteggio e sovrapplicazione.

Intended for applications on both level and vertical surfaces , with good thixotropic properties.

TECHNICAL SPECIFICATIONS

01 12032019	Property	Specification	Units	Method
	Density (20°C)	0,98 - 1,02	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	Thixotropic ($t \geq 180''$)	Sec.	IST 11/08
	Solid Content	31 - 37	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

It is recommended to stir well the product before use.

The product is ready for use, if necessary thin it with water. La diluizione del prodotto è stabilita all'atto dell'applicazione in funzione dei parametri applicativi presenti, consigliate diluizioni minime inferiori all'1%. Miscelare bene il prodotto dopo la diluizione.

For optimal results, product application and drying should happend at higher temperature than 15°C and humidity lower than 80%.

APPLICATION

Dust free	1h e 15' a 20°C (con buona ventilazione)
Touch-free	3h e 15' a 20°C (con buona ventilazione)
Sandable	After 5 hours at 20°C (with good ventilation)
Stacking	24h at 20°C (with good ventilation)
Amount for single layer.	130 / 160 micron

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between 4°C and 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.