

# TECHNICAL DATA SHEET

**CODE:** ANT0494

**NAME:** ANT0494 - PORENFILLER ESCHE GRAUBRAU WB

**GROUP:** WATER-BASED PORE FILLER

## CHARACTERISTICS

Water-based pore filler to be applied with a spray gun on wooden veneer, characterised by fast drying, used to increase the marking of the pore.

To protect this stain polyurethane varnish, "nitro" varnish, polyester varnish or water-based varnish can be applied.

## TECHNICAL SPECIFICATIONS

ANT0494	Property	Specification	Units	Method
	Density (20°C)	1,03 - 1,07	gr/cc	IST 11/01
	Solid Content	25,0 - 29,0	%	IST 11/06

*The values describe the typical properties of the product. Technical Specifications are available upon request.*

## USE

The product is ready for use. Apply with a spray gun having a nozzle from 1,3 to 1,5 millimeters and with a pressure of 2 to 3 bar. Remove excess material by wipe (if wet) or sanding (after dry).

It is recommended to stir well the product before and during use.

## APPLICATION

Recommended amount	30 - 50 gr/m <sup>2</sup> (recommended)
Dust free	About 20' @ 20°C (with good ventilation)
Overcoating	After 4 hours at 20°C (with good ventilation)

## STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between 4°C and 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 20 Kg; for other requests a feasibility evaluation will be made.

## SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.

**Sigmar Vernici s.r.l.** - Via Palmarina 62/1 - 33048 San Giovanni al Natisone - (UD) ITALY - ☎ Phone: +39 0432 756261 - 📠 Fax: +39 0432 756630 - ✉ [info@sigmarvernici.com](mailto:info@sigmarvernici.com) - 🌐 [www.sigmarvernici.com](http://www.sigmarvernici.com)