



CODE: APV0013

NAME: APV0013 - ACCELERANTE

GROUP: ACCELERATOR ADDITIVE

CHARACTERISTICS

Accelerating additive for applications in the field of polyurethane products for industry. Characterized by specific properties such as increased catalyst speed and stabilization of conductivity. Ideal in combination with polyurethane sealers.

TECHNICAL SPECIFICATIONS

APV0013	Property	Specification	Units	Method
	Density (20°C)	0,86 - 0,90	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 11	Sec.	IST 11/08
	Solid Content	9 - 11	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

Add The Accelerator to the polyurethane coating product in quantities from 1 to 5% on part A.

This limit must never be exceeded in order to avoid problems of adhesion or cracking of the paint film.

The added amount depends on the normal drying speed of the product and is however deductible through practical tests.

The product decreases the pot-life of polyurethane and acrylic systems.

APPLICATION

The application characteristics can only be evaluated in combination with the paint that is used.

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between 4°C and 40°C) that is not subject to abrupt temperature excursions.

Standard pack size is 1 Kg. For other specific requirements a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.

Sigmar Vernici S.r.l. - Via Palmarina 62/1 - 33048 San Giovanni al Natisone - (UD) ITALY - 🖀 Phone: +39 0432 756261 - 🕹 Fax: +39 0432 756630 - 🖃 info@sigmarvernici.com - 🖄 www.sigmarvernici.com