

TECHNICAL DATA SHEET

CODE: APV0100

NAME: APV0100 - PRIMER ADESIONE VETRO

GROUP: PAINT ADDITIVE

CHARACTERISTICS

The APV0100 additive is used for solvent-based paints to increase their adhesion to glass and metal.

TECHNICAL SPECIFICATIONS

APV0100	Property	Specification	Units	Method
	Density (20°C)	1,05 - 1,09	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 11	Sec.	IST 11/08

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

The APV0100 additive is added to the paint product at the time of use in quantities varying from 1 to 2% by weight and these limits must not be exceeded so as to not incur cracking problems in the paint film. It is recommended to stir it in well for 5 minutes during its addition.

Surplus material must not be re-used, given that the APV0100 loses its adhesion characteristics after 12 hours.

APPLICATION

The application characteristics can only be evaluated in combination with the paint that is used.

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between 4°C and 40°C) that is not subject to abrupt temperature excursions.

Standard pack size is 1 Kg. For other specific requirements a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.