

# TECHNICAL DATA SHEET

**CODE:** CCS0198

**NAME:** CCS0198 - CONCENTRATO DUNKELBRAUN FUR PMMA

**GROUP:** CONCENTRATED PIGMENT PASTE

## CHARACTERISTICS

Concentrated pigmented pastes for applications on wood or woody materials, to dilute with solvents. Suitable for retouching and correcting wood defects.

## TECHNICAL SPECIFICATIONS

CCS0198	Property	Specification	Units	Method
	Density (20°C)	0,87 - 0,91	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	9 - 12	Sec.	IST 11/08
	Solid Content	3,0 - 5,0	%	IST 11/06

*The values describe the typical properties of the product. Technical Specifications are available upon request.*

## USE

The CCS0198 is a concentrated pigment paste intended to retouch and correct the wood defects. To be used directly on wood.

Thin the product depending on the correction is desired. Apply with a spray gun having a nozzle from 0.5 to 1.0 millimeters and with a pressure of 2 to 3 atmospheres.

It is recommended to stir well the product before and during use.

## APPLICATION

Dust free	About 15' at 20°C (with good ventilation)
Time before Overcoating	After about 4 hours at 20°C (with good ventilation)

## STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 30°C) that is not subject to abrupt temperature excursions.

Standard pack size is 1 Kg. For other specific requirements a feasibility evaluation will be made.

## SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.