

TECHNICAL DATA SHEET

CODE: FPP0554

NAME: FPP0554 - FONDO PUR BIANCO

GROUP: COLOURED POLYURETHANE PRIMER

CHARACTERISTICS

White pigmented polyurethane primer, for application with a normal or electrostatic spray gun, on wood or woody materials, it is characterised by good coverage and fast drying. Developed mainly for use on MDF due to its good adhesion and elasticity.

TECHNICAL SPECIFICATIONS

FPP0554	Property	Specification	Units	Method
	Density (20°C)	1,32 - 1,36	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	130 - 150	Sec.	IST 11/08
	Solid Content	67 - 71	%	IST 11/06
CVP0234	Property	Specification	Units	Method
	Density (20°C)	0,95 - 0,99	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	9,0 -11,0	Sec.	IST 11/08
	Solid Content	25 - 29	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

Harden the primer with the hardener CVP0234 at 40% by weight; subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 5-10% by weight.

APPLICATION

Dust free	About 20 'at 20 ° C (with good ventilation)
Touch-free	About 30' at 20°C (with good ventilation)
Pot-Life	About 3 hours at 20°C (with good ventilation)
Sandable	After 3 - 4 hours at 20°C (with good ventilation)
Amount for single layer.	100 - 120 gr/m ²
Overcoating	Matt and glossy polyurethanes

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.