

TECHNICAL DATA SHEET

CODE: FPT0067

NAME: FPT0067 - FONDO PUR TRASPARENTE

GROUP: CLEAR POLYURETHANE PRIMER

CHARACTERISTICS

Clear polyurethane primer, for application with a normal or electrostatic spray gun, on wood or woody material, characterised by very good coverage, fast drying, excellent sanding and fast overcoating. Intended for closed-pore and open-pore applications.

TECHNICAL SPECIFICATIONS

| FPT0067 | Property | Specification | Units | Method |
|---------|------------------------------|---------------|-------|-----------|
| | Density (20°C) | 0,94 - 0,98 | gr/cc | IST 11/01 |
| | Viscosity, Ford Cup 4 (20°C) | 90 - 105 | Sec. | IST 11/08 |
| | Solid Content | 43 - 47 | % | IST 11/06 |
| CVP0126 | Property | Specification | Units | Method |
| | Density (20°C) | 0,94 - 0,98 | gr/cc | IST 11/01 |
| | Viscosity, Ford Cup 4 (20°C) | 09 - 11 | Sec. | IST 11/08 |
| | Solid Content | 26 - 30 | % | IST 11/06 |

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

To harden the primer, use the hardener CVP0126 at 50% by weight; subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 20% by weight.

As an alternative to CVP0126 it is always possible to use the CVP0163 at 50% by weight, which can be used as the sole catalyst for primers and finishes.

APPLICATION

| | |
|--------------------------|---|
| Dust free | 15' at 25°C |
| Pot-Life | Approx. 2 hours |
| Sandable | After 3 hours at 25°C (with good ventilation) |
| Amount for single layer. | 100 - 120 gr/m ² |
| Overcoating | Matt and glossy polyurethanes |

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.