

# TECHNICAL DATA SHEET

**CODE:** IAI0012

**NAME:** IAI0012 - AQUIDOL ADJUSTMENT

**GROUP:** CONVERTER FOR WATER BASED STAINS

## CHARACTERISTICS

Vehicle/Converter to produce Water-Based stains and hues, for applications, by spraying on wood or wooden materials, characterised by a good drying speed and good coatability.

## TECHNICAL SPECIFICATIONS

IAI0012	Property	Specification	Units	Method
	Density (20°C)	1,00 - 1,04	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	9 - 11	Sec.	IST 11/08
	Solid Content	10,0 - 12,0	%	IST 11/06

*The values describe the typical properties of the product. Technical Specifications are available upon request.*

## USE

It is recommended to stir well the product before use.

Add to the product the TAI series patinas and/or the CCA series concentrate Dyes in the rate suitable for obtaining the desired shade of color. Stir well after adding.

For optimal results, product application and drying should happen at higher temperature than 15°C and humidity lower than 80%.

## APPLICATION

Dust free	About 1h at 20°C (with good ventilation)
Deep drying	About 4h at 20°C (with good ventilation)
Overcoating	After about 5 hours at 20°C (with good ventilation)

## STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between 4°C and 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

## SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.