

# TECHNICAL DATA SHEET

**CODE:** IMT0018

**NAME:** IMT0018 - ISOLANTE PER LEGNI ESOTICI

**GROUP:** SEALER FOR EXOTIC WOODS

## CHARACTERISTICS

Transparent sealer based on saturated polyester resins, for spray applications, characterised by good drying speed and suitable for fixing on exotic woods.

## TECHNICAL SPECIFICATIONS

IMT0018	Property	Specification	Units	Method
	Density (20°C)	0,90 - 0,94	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	8 - 12	Sec.	IST 11/08
	Solid Content	20,0 - 24,0	%	IST 11/06
CVP0063	Property	Specification	Units	Method
	Density (20°C)	0,92 - 0,96	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	8 - 11	Sec.	IST 11/08
	Solid Content	24,0 - 28,0	%	IST 11/06

*The values describe the typical properties of the product. Technical Specifications are available upon request.*

## USE

Harden the transparent sealer IMT0018 with the hardener CVP0063 at 100% by weight; subsequently thin it with DPV0027.

The thinning of the product is established at the time of application according to the application parameters present, recommended at 20% by weight.

## APPLICATION

Pot-Life	About 2 hours at 20°C
Dust free	About 20' @ 20°C (with good ventilation)
Overcoating	After 6 hours at 20 °C

## STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between + 4°C and + 30°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

## SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.