

TECHNICAL DATA SHEET

CODE: ISI XXXX

NAME: ISI XXXX TINTE A SPRUZZO A SOLVENTE

GROUP: TINTE A SPRUZZO A SOLVENTE

CHARACTERISTICS

SCHEDA TECNICA PROVVISORIA. la presente scheda tecnica si riferisce ad un prodotto sperimentale, le cui caratteristiche e specifiche potrebbero variare rispetto al futuro prodotto Standard.

Tinte pigmentate a base solvente, per applicazione sia a spruzzo che a straccio su legno o materiali legnosi, caratterizzate da una buona rapidità di essiccazione e ottima sovraverniciabilità. Available in various colour tones.

TECHNICAL SPECIFICATIONS

ISI XXXX	Property	Specification	Units	Method
	Viscosity, Ford Cup 4 (20°C)	08 - 12	Sec.	IST 11/08
	Solid Content	1,0 - 10,0	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

The product is ready for use. It is recommended to stir well the product before use.

Apply by spraygun with nozzle of 1.3 - 1.6 mm and pressure of 2.0-3.0 bar.

APPLICATION

Dust free	About 15' at 20°C (with good ventilation)
Overcoating	After at least 4 hours at 20°C (with good ventilation)

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between 4°C and 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.