

# TECHNICAL DATA SHEET

**CODE:** KLPT125

**NAME:** KLPT125 - CONVERTER PUR LUCIDO TRASPARENTE

**GROUP:** GLOSSY POLYURETANE CONVERTER

## CHARACTERISTICS

Glossy clear polyurethane Converter, for application with normal or electrostatic spray gun, on wood or woody material characterised by good verticality, excellent filling, fast drying time and surface hardness.  
Colourable in various shades with the addition of PPT series products up to 25% by weight.

## TECHNICAL SPECIFICATIONS

KLPT125	Property	Specification	Units	Method
	Density (20°C)	0,98 - 1,02	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	35 - 45	Sec.	IST 11/08
	Solid Content	48 - 52	%	IST 11/06
CVP0172	Property	Specification	Units	Method
	Density (20°C)	0,99 - 1,03	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 12	Sec.	IST 11/08
	Solid Content	37 - 41	%	IST 11/06

*The values describe the typical properties of the product. Technical Specifications are available upon request.*

## USE

Add the PPT series products to the KLPT125 in the opportune ratio to obtain the deired shade of color, up to a maximum of 25% by weight. Stir well after adding. Harden the converter mixture at 100% by weight with the CVP0172 hardener, subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 20% by weight.

When a better product spreading is required, it is recommended to add a small amount of retardant thinner DPV0026 to the mix.

As an alternative, it is possible to use the CVP0096 hardener at 50% by weight for an anti-yellowing effect or at 100% by weight when are required brushing and polishing processes

## APPLICATION

Dust free	About 15' at 20°C (with good ventilation)
Pot-Life	Around 4 hours at 20°C (with good ventilation)
Stacking	After 24 hours at 20°C (with good ventilation)
Gloss Level	95 - 100 Gloss Units (without PPT series dyes)

## STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

## SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.