

TECHNICAL DATA SHEET

CODE: LPT0008

NAME: LPT0008 - LUCIDO PUR TRASPARENTE

GROUP: TRANSPARENT PUR VARNISH

CHARACTERISTICS

Solvent-based clear polyuretanic paint, for application with a normal or electrostatic spray gun, characterised by good filling and fast drying.

Intended for use on level surfaces, for interiors applications.

TECHNICAL SPECIFICATIONS

LPT0008	Property	Specification	Units	Method
	Density (20°C)	0,98 - 1,02	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	35 - 45	Sec.	IST 11/08
	Solid Content	46 - 56	%	IST 11/06
CVP0172	Property	Specification	Units	Method
	Density (20°C)	0,99 - 1,03	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 12	Sec.	IST 11/08
	Solid Content	37 - 41	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

To harden the LPT0008, use the hardener CVP0172 at 100% by weight; subsequently, thin it with DPV0006.

The thinning of the product is established at the time of application according to the application parameters present, recommended at 20% by weight.

When a better product spreading is required, it is recommended to add a small amount of retardant thinner DPV0026 to the mix.

APPLICATION

Pot-Life	Approx. 12 hours at 20°C
Dust free	15' at 25°C
Gloss Level	90 - 100 Gloss units
Stacking	After 24 hours

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions. Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.