

TECHNICAL DATA SHEET

CODE: OPP 01_21012021

NAME: OPP 01_21012021 - OPACO PUR BIANCO - 30

GROUP: PIGMENTED MATT PUR FINISH

CHARACTERISTICS

Finitura poliuretanica opaca bianca a base solvente, for application with a normal or electrostatic spray gun, on wood or woody material, caratterizzata da una buona verticalità, buon riempimento, rapidità di essiccazione e durezza superficiale.

SCHEDA TECNICA PROVVISORIA. la presente scheda tecnica si riferisce ad un prodotto sperimentale, le cui caratteristiche e specifiche potrebbero variare rispetto al futuro prodotto Standard.

TECHNICAL SPECIFICATIONS

OPP 01_210 12021	Property	Specification	Units	Method
	Density (20°C)	1,20 - 1,24	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	Thixotropic (t ₉₀ = 180")	Sec.	IST 11/08
	Solid Content	62 - 68	%	IST 11/06
CVP0200	Property	Specification	Units	Method
	Density (20°C)	0,98 - 1,02	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	10 - 12	Sec.	IST 11/08
	Solid Content	26 - 30	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

Catalizzare il prodotto al 50% in peso con il catalizzatore CVP0200, subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 20% by weight.

Apply with a spray gun having a nozzle from 1,3 to 1,5 millimeters and with a pressure of 2 to 3 bar.

APPLICATION

Pot-Life	About 3 hours at 20°C (with good ventilation)
Dust free	About 15' at 20°C (with good ventilation)
Stacking	After 24 hours at 20°C (with good ventilation)

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.