

TECHNICAL DATA SHEET

CODE: PPS0461

NAME: PPS0461 - PIGMENT CONCENTRATE DARK OAK

GROUP: CONCENTRATED PIGMENT PASTE

CHARACTERISTICS

Solvent-based brown pigment paste for use in the wood/automotive industry for the preparation, in combination with N-butyl acetate, of ANT0445 Patina Dark OAK G0X PMMA.

TECHNICAL SPECIFICATIONS

PPS0461	Property	Specification	Units	Method
	Density (20°C)	0,99 - 1,03	gr/cc	IST 11/01
	Solid Content	26 - 30	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

Add the concentrate pigment paste to the N-butyl acetate in ratio 1:10. Stir well after adding with mechanical stirrer at approx. 1000 rpm for min 10'.

APPLICATION

The mixing product is to use in accordance to the process instruction of ANT0445 Patina Dark OAK G0X PMMA.

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 30°C) that is not subject to abrupt temperature excursions.

Standard pack size is 1 Kg. For other specific requirements a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.