

TECHNICAL DATA SHEET

CODE: SOE2020

NAME: SOE2020 - SYNTOWOOD FINITURA G.20

GROUP: SEALER FOR OUTDOOR

CHARACTERISTICS

Single-component matt clear paint, solvent-based, based on urethane resins modified with siccative oils. Suitable for exterior and interior finishes, for application with a normal or electrostatic spray gun, on wood or woody materials.

TECHNICAL SPECIFICATIONS

SOE2020	Property	Specification	Units	Method
	Density (20°C)	0,90 - 0,94	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	255 - 305	Sec.	IST 11/08
	Solid Content	50 - 60	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

The product is ready for use; thin with white spirit to achieve the appropriate application viscosity. The thinning of the product is established at the time of application according to the application parameters present, recommended at 10% by weight. After about 8 hours from the application of first coat, it is possible to sand and apply the second coat.

APPLICATION

Amount for single layer.	150 - 300 microns
Dust free	About 90'-120' at 20°C (with good ventilation)
Touch free	After about 4 hours at 20°C (with good ventilation)
Sanding	After about 8 hours at 20°C (with good ventilation)
Stacking	After 24 hours (with good ventilation)
Gloss Level	17 - 23 Gloss Units

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.

Sigmar Vernici s.r.l. - Via Palmarina 62/1 - 33048 San Giovanni al Natisone - (UD) ITALY - ☎ Phone: +39 0432 756261 - 📠 Fax: +39 0432 756630 - ✉ info@sigmarvernici.com - 🌐 www.sigmarvernici.com