

# TECHNICAL DATA SHEET

**CODE:** UPT Series

**NAME:** UPT Series - TREPPENLACKE

**GROUP:** STAIR PAINT

## CHARACTERISTICS

Solvent-based clear multilayer paint, for application with spray, brush and roller, characterised by a high resistance to mechanical stresses. Specifically intended for painting interior stairs, available in two opacity levels: 80 and 25 Gloss.

## TECHNICAL SPECIFICATIONS

UPT Series	Property	Specification	Units	Method
	Density (20°C)	0,97 - 1,02	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	54 - 66	Sec.	IST 11/08
	Solid Content	42 - 47	%	IST 11/06
CVP0218	Property	Specification	Units	Method
	Density (20°C)	0,89 - 0,93	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 11	Sec.	IST 11/08
	Solid Content	23 - 27	%	IST 11/06
CVP0219	Property	Specification	Units	Method
	Density (20°C)	0,96 - 1,00	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 11	Sec.	IST 11/08
	Solid Content	23 - 27	%	IST 11/06

*The values describe the typical properties of the product. Technical Specifications are available upon request.*

## USE

Harden the product at 100% by weight with the hardener CVP0219, subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 10% by weight. In the summer season and in the presence of high temperatures, it is recommended to use the CVP0218 always at 100% by weight, as an alternative to the CVP0219, to allow a good distension of the product.

## APPLICATION

Pot-Life	About 2 - 3 hours at 20°C (with good ventilation)
Suggested amount	90 - 120 Gr/m <sup>2</sup>
Dust free	About 20' - 25' at 20°C (with good ventilation)
Touch-free	About 60' - 50' at 20°C (with good ventilation)
Sanding	After 2 hours at 20°C (with good ventilation)
Stacking	After 24 hours at 20°C (with good ventilation)

## STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions. Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

## SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.