

TECHNICAL DATA SHEET

CODE: VES0277

NAME: VES0277 - FINITURA MADREPERLA

GROUP: MOTHER-OF-PEARL EFFECT

CHARACTERISTICS

2K acrylic solvent-based Top-Coat, for normal and electrostatic spray applications, on wooden and plastic materials, colourless, very durable, lends a precious reflection similar to a mother-of-pearl glare to the product. Intended for interior applications.

TECHNICAL SPECIFICATIONS

VES0277	Property	Specification	Units	Method
	Density (20°C)	0,91 - 0,95	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	90 - 110	Sec.	IST 11/08
	Solid Content	21 - 25	%	IST 11/06
CVP0175	Property	Specification	Units	Method
	Density (20°C)	0,94 - 0,98	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	09 - 13	Sec.	IST 11/08
	Solid Content	28 - 32	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

Harden the VES0277 at 20% with CVP0175, subsequently thin it with DPV0006. The thinning of the product is established at the time of application according to the application parameters present, recommended at 50% by weight. It is recommended to stir well the product after the thinning.

To get the best performance in terms of design and adhesion, the interaction with other supporting products is of the utmost importance, please contact our technical service.

APPLICATION

Suggested amount	90 - 120 gr/m ²
Dust free	About 15' at 20°C (with good ventilation)
Overcoating interval	From a minimum of 3' to a maximum of 6'
Stacking	After 24 hours at 20°C (with good ventilation)

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between + 4°C and + 30°C) that is not subject to abrupt temperature excursions. Standard packaging size of 5 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.