

TECHNICAL DATA SHEET

CODE: VES0326

NAME: VES0326 - METAL CHROME EFFECT

GROUP: CHROMIUM PLATING EFFECT

CHARACTERISTICS

Single-component solvent-based coat, for spray applications on various types of materials, able to confer to the surface a look similar to chrome.. Medium resistant to scratches, wear and thermal shock, according to the products used as topcoat. Non-yellowing product suitable for both indoor and outdoor items, depending on the amount of cycles used.

TECHNICAL SPECIFICATIONS

VES0326	Property	Specification	Units	Method
	Density (20°C)	0,87 - 0,91	gr/cc	IST 11/01
	Viscosity, Ford Cup 4 (20°C)	11 - 15	Sec.	IST 11/08
	Solid Content	0 - 2	%	IST 11/06

The values describe the typical properties of the product. Technical Specifications are available upon request.

USE

The product is ready for use; Apply with a spray gun having a nozzle from 1,0 to 1,4 millimeters and with a pressure not higher than 3 bar.

For best results it is recommended to apply the product on a black and glossy primer suitable for the material on which you want to apply the product. The application of topcoat is recommended after at least 48 hours.

APPLICATION

Suggested amount	10 - 20 gr/m ²
Dust free	About 15' at 20°C (with good ventilation)

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between + 4°C and + 30°C) that is not subject to abrupt temperature excursions. Standard pack size is 1 Kg. For other specific requirements a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.