

TECHNICAL DATA SHEET

CODE: VES1000

NAME: VES1000 - GLASSLACKE GIALLO

GROUP: PIGMENTED MATT PUR FINISH

CHARACTERISTICS

Solvent-Based pigmented matt polyurethane finish, specific for glass, yellow coloured, for application with a normal or electrostatic spray gun, characterised by good filling, fast drying and surface hardness.
The finish is designed to be used exclusively in combination with the additive for glass, APV100.

TECHNICAL SPECIFICATIONS

The technical specifications are supplied on request, according to colour.

USE

For the optimal choice of the hardener, and the percentage by weight to be used, depending on the desired result or the end use of the item, please contact our technical service.

To achieve adhesion on glass it is necessary to add the additive APV100 to the VES1000, up to a maximum of 2% by weight, before the use. It is recommended to stir it well for 5 minutes after its addition.

Surplus material must not be re-used, given that the APV0100 loses its adhesion characteristics after 12 hours.

APPLICATION

Pot-Life	About 2 hours at 20°C (with good ventilation)
Dust free	About 25' at 20°C (with good ventilation)
Stacking	After 24 hours at 20°C (with good ventilation)

STORAGE AND PACKAGING PRECAUTIONS

Keep it tightly sealed in its original container in a cool environment (between - 5°C and + 40°C) that is not subject to abrupt temperature excursions.

Standard packaging size of 25 Kg; for other requests a feasibility evaluation will be made.

SAFETY PRECAUTIONS

The product is intended for professional use only, refer to the Safety Data Sheet.

MOD. 11 - 08 (Rev. 1 - 06/2016)

The data shown refers to laboratory tests, in practical applications these can change slightly according to the working conditions. The user must anyway check the suitability of the product for its expected use, taking upon himself all responsibility arising from its use. Sigmar reserves the right to introduce technical changes without prior notice.